

RELIABILITY MONITOR

PRODUCT	MONITOR DATE	DATE CODE	ASSEMBLY FACILITY	ASSEMBLY LOT NO	PROCESS TYPE	PACKAGE TYPE
DS1259	Mar-96	9531 C2	CARSEM	DM504173ABH	2.0μ NITRIDE	16 PDIP

STRESS/JOB NO.

READPOINT (Sample Size/No. of Fails)

Infant / High Voltage Life 125°C, 7.0 V. P-17075, P-17110	<table border="0"> <tr> <td><u>48 Hr</u></td> <td><u>336 Hr</u></td> <td><u>1KHr</u></td> <td><u>*Failure Rate</u></td> </tr> <tr> <td>231/0</td> <td>77/0</td> <td>77/0</td> <td>30 Fits</td> </tr> </table>	<u>48 Hr</u>	<u>336 Hr</u>	<u>1KHr</u>	<u>*Failure Rate</u>	231/0	77/0	77/0	30 Fits
<u>48 Hr</u>	<u>336 Hr</u>	<u>1KHr</u>	<u>*Failure Rate</u>						
231/0	77/0	77/0	30 Fits						

*Chi Squared Method, 60% C. L., 55°C & 5.5V; Temperature Derating: Ea = 0.7 ev; Voltage Derating B = 1.0

Temp Cycle -55°C to +125°C P-17111	<table border="0"> <tr> <td><u>300 ~</u></td> <td><u>1K ~</u></td> <td><u>Cum %</u></td> </tr> <tr> <td>39/0</td> <td>39/0</td> <td>0.0%</td> </tr> </table>	<u>300 ~</u>	<u>1K ~</u>	<u>Cum %</u>	39/0	39/0	0.0%
<u>300 ~</u>	<u>1K ~</u>	<u>Cum %</u>					
39/0	39/0	0.0%					

Biased Moisture 85°C/85% RH, 5.5 V. P-17112	<table border="0"> <tr> <td><u>274 Hr</u></td> <td><u>959 Hr</u></td> <td><u>Cum %</u></td> </tr> <tr> <td>77/0</td> <td>77/0</td> <td>0.0%</td> </tr> </table>	<u>274 Hr</u>	<u>959 Hr</u>	<u>Cum %</u>	77/0	77/0	0.0%
<u>274 Hr</u>	<u>959 Hr</u>	<u>Cum %</u>					
77/0	77/0	0.0%					

Autoclave 121°C/100% RH, 2 Atmos P-17113	<table border="0"> <tr> <td><u>96 Hr</u></td> <td><u>Cum %</u></td> </tr> <tr> <td>38/0</td> <td>0.0%</td> </tr> </table>	<u>96 Hr</u>	<u>Cum %</u>	38/0	0.0%
<u>96 Hr</u>	<u>Cum %</u>				
38/0	0.0%				

Failure Mode

Failure Analysis